

FC/S Series
THERMOLAST® K

The FC/S Series consists of extremely soft materials for applications with food contact. They are available in natural-colored, translucent and highly transparent versions. The materials have a dry feel.

Typical applications

- Baits
- Cushioning
- Fun articles
- Function and design elements
- Grip applications
- Protectors
- Toys

Material advantages

- Adhesion to PP
- Applications with food contact
- Code of Federal Regulations, Title 21 (CFR 21) "FDA"
- Dry surface
- Easy processing
- EN71/3
- Excellent mechanical properties at low hardness
- Pleasant surface feel (Soft touch)
- Regulation (EU) No. 10/2011

Processing Method: Injection Molding

	Color / RAL DESIGN	Hardness DIN ISO 27588 (D=6mm) VLRH	Density DIN EN ISO 1183-1 g/cm ³	Tensile Strength ¹ DIN 53504/ISO 37 MPa	Elongation at Break ¹ DIN 53504/ISO 37 %	Tear Resistance ISO 34-1 Methode B (b)(Graves) N/mm
TF0STL	translucent	51	0.870	1.5	800	3.0
TF0STT	transparent	73	0.880	0.5	500	2.0
TF1SNT	natural	74	1.010	2.0	700	4.0
TF1STL	translucent	75	0.880	2.0	750	4.0
TF1STT	transparent	83	0.880	0.7	350	4.0
TF2SNT	natural	83	1.040	3.0	750	8.0
TF2STL	translucent	81	0.880	3.0	700	7.0
TF2STT	transparent	85	0.880	0.7	500	4.0

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.


¹ Deviating from ISO 37 standard test piece S2 is tested with a traverse speed of 200 mm/min.

Info: TF0STT, TF1STT and TF2STT: Risk of blocking due to heat sensibility (important for transport and storage)

All values published in this data sheet are rounded average values.
Specification limits are based on three-fold standard deviation from the average value.

VLRH - Very Low Rubber Hardness

VLRH - Very Low Rubber Hardness (acc. DIN ISO 27588)



Shore A (DIN ISO 7619)	14	7
VLRH (6 mm) (DIN ISO 27588)	83	74

The comparison between Shore A and VLRH is just a reference, below 15 Shore A, the VLRH is more accurate. KRAIBURG TPE uses only the VLRH test method in this hardness range.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.

Processing Guideline Injection Molding

Cylinder temperature	140 - 160 - 180 °C, max. 220 °C (280 - 320 - 360 °F, max. 430 °F)
Hotrunner	Hot runner temperatures: 160 - 180 °C (320 - 360 °F). The runner should be empty after a maximum of 2 - 3 shots.
Injection pressure	200 - 1000 bar (2900 - 14504 psi) (depending on the size and weight of the part).
Injection rate	In general, the fill time should not be more than 1–2 seconds.
Hold pressure	We recommend to derive the optimum hold pressure from determining the solidification point, starting with 40 % - 60 % of the required injection pressure.
Back pressure	20 - 100 bar; if colour batches are used, higher back pressure is necessary.
Screw retraction	If an open nozzle is used processing with screw retraction is advisable.
Mold temperature	25 - 40 °C (77 - 104 °F)
Pre drying	Pre drying of the material is not necessary; if surface moisture forms as a result of changes in temperature, the material should be dried for 2 - 4 hours at 60 - 80 °C (140° F).
Needle valve	The use of a needle valve nozzle is advisable .
Screw geometry	Standard 3-zone polyolefine screw.
Residence time	The residence time is to be set as short as possible with a maximum of 10 minutes.
Cleaning recommendation	For cleaning and purging of the machine it is appropriate to use polypropylene or polyethylene. Machine must be PVC-free.

This datasheet is an extract of the KRAIBURG TPE program. Please contact KRAIBURG TPE to select the compound suitable for the requirements.

Disclaimer: The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication and may be subject to revision as new knowledge and data becomes available. All values reported are typical values based on sample test results and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer. KRAIBURG TPE does not warrant or assume any liability with regards to the use of the information presented in this document.